

IXL Marine Grease - Technical Data

Testing Performed	Method	Result
NLGI Grade	ASTM D 217	2
Thickener Type	-	CSC
Appearance	Visual	Smooth
Color	Visual	Blue
Worked Penetration	ASTM D 217	265 - 295
Drop Point	ASTM D 2265	288° C / 550° F.
Base Oil Viscosity, CST @ 40°C	ASTM D 445	130
Wheel Bearing Leakage, gm	ASTM D 1263	4.0 MAX
Water Washout @ 79° C /175° F, % wt	ASTM D 1264	1.3
Water Washout @ 38° F /100° F, % wt	ASTM D 1264	1.5
Water Spray-off	ASTM D 4049	7.5
Weld Load, kg	ASTM D 2596	800
Load Wear Index	ASTM D 2596	65
Copper Corrosion	ASTM D 1743	1A
Rust Protection	ASTM D 130	Pass
Oil Separation	ASTM D 1742	0.0 %